

Insulating flange connections and insulating screws made in Germany

IsoSeal D200

Flange insulating gasket for operating temperatures up to 200 °C

Applications	Gas / oil / fuels / water / steam / superheated steam / other media on request		
suitable for flanges according to	EN 1092-1 and DIN 2632-2637	ANSI B 16.5 ANSI B 16.47	
Sizes	DN15 to DN900	1/2"-40"	
Pressure	up to PN160	Class150/300/600/900	
Sealing principle	Force shunt Carrier material GRP Sealing medium graphite		
Thickness when installed	4mm (Standard)		
	Special dimensions and thicknesses up to 30mm on request		
Carrier Material (GRP)			

Binder	Ероху
Material	Glasfilamentgewebe
Color	light green / green

	Unit	Value	Test method
Thickness	mm	4,0 - 20	
Density	g/cm³	2,0	ISO 1183/A
Tensile strength	MPa	240	ISO 527
Compressive strength	MPa	500 / 350 / 300	ISO 604
		(23°C /	100 004
		180°C/220 °C)	
Bending strength	MPa	250 / 150	ISO 178
		(120°C /	
		150°C)	
Operating temperature	O°	200	IEC 60216
Maximaltemperatur	O°	220	IEC 60216
Cryogenic	°C	> -60	(others on
			request)
Breakdown voltage (at 90°	Kv	60	ICE 60243
parallel to the layering)		00	102 00240
Dielectric strength	k\//mm	13	IEC 60243
(1min test voltage,			
3 mm thickness)			
Water absorption	mg	30	ISO 62/1

GfD Paulmann GmbH | Fraunhoferstraße 17 | 95448 Bayreuth

Telefon +49 921 / 50 70 5806 | E-Mail gfd@gfd-paulmann.com

Geschäftsführer David Paulmann | USt-IdNr. DE165279146 | HRB 2244 Amtsgericht Bayreuth Bank Raiffeisenbank am Kulm eG | IBAN DE86 7706 9782 0000 0768 05 | BIC GENODEF1SPK



Insulating flange connections and insulating screws made in Germany

IsoSeal GGR

Data Sheet (Page 2 of 2)

Sealing material

Material	Grafit
Color	anthracite

	Unit	Value	Test method
Thickness	mm	1,5	
Density	g/cm³	1,25	DIN E28090-
			2
Pressure resistance	MPa	> 45	DIN 52913
Pressing	%	> 20	ASTM F36A
Springback	%	> 12	ASTM F36A
Ascherest	%	≤ 2	DIN 51903
Chloride Content	ppm	≤ 50	
Min. surface pressure	MPa	15	
Max. surface pressure	MPa	120	
Max. continuous temperature	O°	500	

Approvals DVGW NG-512BL0367

RemarksSealing substrates made of epoxy resin-bonded glass filament
laminates are highly resistant to most chemicals, fuels, oils, water,
hot water and water vapour.
Exceptions: Strong alkalis, acids and oxidizing agents.

Expanded graphite has excellent sealing properties, is not subject to media restrictions and is resistant to aging and temperature up to 500 °C and in cryogenic applications to at least -60 °C.

Sketch

for flanges DN100 PN10-16



As of: January 2025

 GfD Paulmann GmbH | Fraunhoferstraße 17 | 95448 Bayreuth

 Telefon +49 921 / 50 70 5806 | E-Mail gfd@gfd-paulmann.com

 Geschäftsführer David Paulmann | USt-IdNr. DE165279146 | HRB 2244 Amtsgericht Bayreuth

 Bank Raiffeisenbank am Kulm eG | IBAN DE86 7706 9782 0000 0768 05 | BIC GENODEF1SPK